

# **Product Data Sheet**

## #837 Striped

#### **ENGINEER GRADE REFLECTIVE**

### PRODUCT INFORMATION GUIDE

Application(s): Our Engineer Grade reflective sheeting is a high quality, durable, enclosed lens

retroreflective material. This reflective sheeting offers exceptional value for permanent traffic signage applications. Meets applicable requirements for engineer grade sheeting applications for Type 1 retroreflective sheeting as set

forth in ASTM D 4956

Adhesive: Permanent Pressure Sensitive (Class 1)

Face Film: High Gloss

Liner: White Polyethylene Coated Paper

**Tape Application:** Minimum application temperature 4°C (40°F)

Surface must be clean and free from dust, dirt, oil, wax, silicone.

**Clean tape** surface with a mild soap and rinse with fresh water.

**Shelf Life:** One year, when stored at 73°F (23°C), 50% +/- 5% relative humidity.

| Property:   | Test Method: | Measurement:  |  |  |  |  |
|---|--------------|---|--|--|--|--|
| Outdoor Durability<br>Operational Temp.<br>Typical Film Caliper<br>Specifications |              | 7 years when properly processed and applied (vertical) (-40°C to 82°C) -40°F to 180°F 4.5 - 5.5 mils Meets all other requirements set forth in ASTM D 4956 including shrinkage, flexibility, liner removal, adhesion, |  |  |  |  |
|   |              | impact resistance, specular gloss and outdoor weathering  |  |  |  |  |

#### **Photometric Performance:**

Exceeds Types III and IV values per ASTM D 4956. Minimum Coefficient of Retroreflectivity (R<sub>A</sub>) (cd/lx/m<sup>2</sup>)

| Observation Angle (°) | Entrance Angle (°) | White | Yellow | Orange | Green | Red | Blue |
|-----------------------|--------------------|-------|--------|--------|-------|-----|------|
| 0.2                   | -4                 | 70    | 50     | 25     | 9     | 14  | 4    |
| 0.2                   | 30                 | 30    | 22     | 7      | 3.5   | 6   | 1.7  |
| 0.5                   | -4                 | 30    | 25     | 13     | 4.5   | 7.5 | 2    |
| 0.5                   | 30                 | 15    | 13     | 4      | 22    | 3   | 0.8  |

The physical and performance characteristics shown are averages obtained from tests recommended by ASTM, government agencies or our own procedures. A particular roll may vary slightly from these averages and it is recommended that the purchaser determine the suitability for his own purpose.